

BIO FELT[®] 1 E LIGHT

VAPOUR BARRIER BITUMINOUS UNDERLAY

Talc finishing

Made in Italy by Silcart

CE CLASS: 1P (internal code)

CHECKED CHARACTERISTICS	UNIT OF MEASURE	VALUE
Mass per unit area	g/m ²	500±5%
Tensile Strength	N/5cm	MD: 280±15% CD: 200±15%
Resistance to water penetration		Class W1
UV Resistance		4 months
Water vapour transmission property	m	Sd=50

Product subject to CE mark according to EN 13859-1

Rev.02 07/12