

TEKAFLEX

MS15

PROPERTIES

- Excellent adhesion on most construction materials - concrete, brick, plasterboards, steel, ceramics, metal, most types of plastic, Styrofoam etc.).
- Good output even at low temperatures.
- Does not slump in vertical joints.
- Excellent mechanical properties, good elasticity and flexibility.
- Environmentally friendly; it is solvent, isocyanate and silicone free.
- It can be applied on moist surfaces.
- Chemically neutral and odourless.
- Can be painted with most paints and varnishes on the basis of epoxy, polyurethane and water.
- Shrinkage during hardening process below 1,5%.
- Resistant to atmospheric effects, UV-light and ageing.
- Does not cause corrosion.
- Chemical resistance
 - Good chemical resistance to: water, aliphatic solvents, mineral oils, fat, low concentration inorganic acids and bases;
 - Poor chemical resistance or not resistant to: aromatic solvents, concentrated acids, chlorinated hydrocarbons.
- Colour: grey RAL 7030 and white; others available on demand.

TESTS AND CERTIFICATES

EN 15651-1:2012 F-EXT-INT-CC,
 EN 15651-4:2012 PW-INT,
 GEV-EMICODE EC-1 PLUS (very low emission),
 ISO 11600.

USE

- For weather sealing of dilatation joints and wall penetrations in construction industry, between prefabricated construction elements, in greenhouses etc.
- Useful in places where joints have to be painted or where silicone sealants are not suitable.
- For sealing structures subject to vibrations.
- For sealing joints between window frames, doors, plasterboards and concrete elements.
- For sealing roof light domes.
- The product is recommended for sealing joints in rooms where mould can form.
- For sealing joints in silos, containers and vacuum system.
- For remedying consequences of leakage.
- For sealing and gluing different materials in the automobile and shipbuilding industry.
- For elastic gluing and sealing in power generation industry.



Tekaflex MS15

is a one-component sealant on the basis of a hybrid MS polymer. Due to its high elasticity it is suitable for sealing dilatations joints, wall penetrations and joints in general.



Adhesive



For interior and exterior use



Easily painted

TEHNICAL DATA

Fresh sealant

Base		hybrid MS polymer
Appearance		paste
Curing mechanism		by air humidity
Specific gravity		1470±10kg/m ³
Skin formation time	23°C/50% rel. humid	20–30 min.
Hardening time	23°C/50% rel. humid	2–3 mm/day
Application temperature		between +5°C and +30°C

Cured sealant

Hardness Shore A	ISO 868	15–20
Change in volume	ISO 10563	<1,5%
Tensile strength	ISO 8339	0,50–0,70MPa
Module E 100%	ISO 8339	0,20–0,40MPa
Elongation at break	ISO 8339	250–350%
Tensile strength	ISO 37	1,00–1,30MPa
Elongation at break	ISO 37	350–450%
Temperature resistance		between -40°C and +90°C

APPLICATION

Prior to use it is recommended to perform an adhesion test to verify adhesion of the sealant to the substrate.

Surface preparation

- The surface of the joint must be dry, hard, clean, dust and fat free.
- Remove all separated and badly attached pieces.

Joint and cartridge preparation

- For good adhesion onto porous materials use Primer KVZ 16 (see technical data sheet Primers).
- If you want joints to look nice tape the edges with a masking tape.
- Cut the cartridge at the top and screw on the nozzle, which has to be cut according to the width of the joint and placed in the gun. During work interruption release the handle on the gun and pull the piston back.
- The sealant should be applied as evenly as possible.
- At the end, use a smoothing tool - a TTK smoothing instrument, or a Smoothing agent soaped finger to level the sealant before the skin starts to form. It is very important to press the sealant well against the surface to be sealed.
- Remove the masking tape before the sealant starts to harden.
- Fresh sealant and tools can be cleaned with the Tekafin cleaner, hardened sealant should be removed mechanically first and then with a cleaner for hardened silicone - Tekapursil S or Apursil.

Correct dimensioning of expansion joints

For optimal elasticity of a sealant the correct ratio width:depth is of extreme importance. The ratio is 2:1, 1:1 maximum. Sealant should not adhere to the bottom of the joint gap but only to its sides. This can be achieved with the use of Tekatrak Back filling tape. The minimum and maximum joint width is 6mm and 30 mm, respectively.

Joint length (mm)	Joint width (mm)					
	6	8	10	12	15	20
6	8,3	6,2	5,0	4,2		
8		4,7	3,7	3,1	2,5	
10			3,0	2,5	2,0	1,5
12				2,1	1,7	1,2
15					1,3	1,0
20						0,75

The table shows how many linear metres of joints we can seal with one 290ml cartridge relative to the width and depth of the joint.

PACKAGING

- 290 ml cartridge
 - 600ml sausage
 - other packagings are available by agreement.
-

STORAGE

15 months in dry space at temperature range between +5°C and +25°C, in originally closed packaging.

HEALTH, SAFETY HANDLING AND DISPOSAL INFORMATION

Additional information on safety, safe handling instructions and personal protective equipment as well as disposal information are available in a safety data sheet. Safety data sheet is available upon request. You can also ask your TKK distributor for a copy.

WARNING

Instructions contained in this document are based on our research and experience, however, due to specific conditions and working methods we recommend that you perform preliminary tests prior to any application of our products.