

### General Description

Glass fiber mesh fabrics combined with specially designed mesh surface treatments can be used in a wide range of applications.

Mesh R 131 is mainly used as one component of external thermal insulation systems. A high quality synthetic coating on the glass yarn protects our mesh against alkaline influences from the adhesives and other materials that are used.

### Technical characteristics

Works Standard: 0326 Glass Fibre Mesh Fabrics

Characteristics	Units Description	R 131 A101N	
		Warp	Weft
Setting	per 100 mm	25 x 2	20,5
Weave		half leno	
Standard Width (1)	cm / individual value	100 or 110	
Roll Length (1)	m / individual value	50	
Treated Fabric Thickness	mm / informative value	0,52	
Loom state Fabric Weight	g/m <sup>2</sup> / informative value	131	
Treated Fabric Weight	g/m <sup>2</sup> / informative value	160	
Combustible Matter Content (LOI)	% of mass / individual value	20	
Treatment type	alkaliresistant without emollient, obstructing yarn drifting		
Square Dimension	mm / informative value	3,5	3,8

(1) Other dimension on request

Tensile strength (TS) and elongation:

Minimum individual tensile strength (N/50 mm) and maximum elongation (%) when reaching minimum tensile strength is ascertained according DIN EN ISO 13934-1 as per below.

	Tensile Strength		Elongation
	Nominal value	Individual value	Average value
Deposition method			
Standard condition	2000 / 2100	1800 / 1800	3,5 / 3,5
3 ions solution (ETAG 004)		1000 / 1050 50 % / 50 %	


### Additional Information

- **Tolerances**
  - Setting: ± 5% in warp and weft
  - Width: ± 1 %
  - Length: -0 % + 2%
  - LOI: ± 4 %
- **Quality inspection**  
The way of quality inspection, taking of the samples and taking over of the material, is according to 0326 works standard
- **Packing:**  
The rolls of fabrics are packed vertically in cardboard, on a wooden pallet. A precise method of packing is mentioned in the works standard for packing
- **Storing:**  
Packed rolls are to be stored in dry rooms. Storing temperature is from -10°C to + 50°C

### Technical Data Sheet

#### Properties

- High mechanical strength
- Excellent dimensional stability
- Compatible with all major facade systems
- Non-flammable fabric



Edited by:  
**ADFORS Construction Products Europe**

Saint-Gobain Vertex  
Sokolovska 106  
CZ – 570 21 Litomyšl  
Tel: + 420 461 651 111  
Fax: + 420 461 612 769  
www.sg-adfors.com

**ADFORS Construction Products Europe** reserves the right to change the information given herein without prior notice

Technical Data Sheet N° 102

Last update: 24/05/2011