

IZOPLAST

waterproofing membrane

Compound

APP

Flexibility

-5°C

Product description: IZOPLAST PES & IZOPLAST MINERAL P are waterproofing membranes made from a polyester fleece reinforcement, that is coated on both sides with plastomer (APP) modified bitumen. IZOPLAST PES is protected on both sides by polymeric sheeting. IZOPLAST MINERAL P is on the upper side protected by mineral granules and on the bottom side by polymeric sheeting. Mineral granules protect it against ageing and UV-light.

Characteristics of the product: IZOPLAST PES meets the demands of the standards EN 13707, EN 13969 Type T. IZOPLAST MINERAL P meets the demands of the standards EN 13707. The APP additions give high resistance against low and higher temperatures. The mechanical characteristics of the polyester fleece give the product high resistance against penetration and tearing.

Characteristic	EN Method	Unit	IZOPLAST		
			PES	MINERAL P	
Reinforcement			polyester		
Surface protection					
Length	1848-1	m	≥ 10/8/7.5*		
Width	1848-1	m	≥ 1		
Straightness	1848-1	20 mm/10m	pass		
Mass per unit area	1849-1	kg/m ²	3/3.5/4/4.5/5	4/4.5	5/5.5
Water tightness	1928/2000	kPa	≥ 60		
Flexibility at low temperature					
• surface	1109	°C	≤ -5		
• bottom					
Flow resistance at elevated temperature	1110	°C	≥ 120		
Resistance to tearing					
• longitudinal	12310-1	N	≥200	NPD	
• transversal			≥200	NPD	
Shear resistance to joints					
• longitudinal	12317-1	N/50 mm	≥600	NPD	
• transversal			≥350	NPD	
Dimensional stability					
• longitudinal	1107	%	≤10.6l		
• transversal			≤ 10.6l		
Water vapour properties	1931	μ	20000		
External fire performance	13501-5	class	F _{ROOF} (t1)		
Reaction to fire	13501-1	class	E		
Chemical resistance	1847/13969 Annex A	-	pass		
Resistance to static loading	12730	kg	≥ 20		
Resistance to impact	12691/A	mm	≥ 1200		
Tensile strength					
• longitudinal	12311-1	N/50mm	≥600	≥500	≥600
• transversal			≥350	≥300	≥350
Elongation					
• longitudinal	12311-1	%	≥ 30		
• transversal			≥ 30		
Flow resistance at elevated temperature against artificial ageing by long term exposure to elevated temperature ((12 weeks at 70°C)	1296/1110	°C	≥ 120		
Adhesion of granules	12039	%	NPD	≤10	
Content of hazardous substances	Annex ZA	/	Does not contain		

Use and installation: IZOPLAST PES, is used regarding the demands of the standards as an intermediate layer in two or more layered flat roof systems which are protected by UV-resistant membrane. It is used for less demanding underground waterproofing systems, i.e, the resistance to ponding water and in two-layer systems of vertical and horizontal waterproofing that are exposed to water pressure.

IZOPLAST MINERAL P, is used in two or more layered flat roof systems as top layer that protect roof from UV light and ageing..

The membranes are installed by torch with 10cm overlaps, which must be waterproof.

Storage and transport: The rolls have to be store in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

Disposal consideration of waste: The carrier is responsible for the correct transport. For the removal of waste of product it is necessary to follow the valid local enviromental regulations.



Number EC certificate of control of quality: **1404 – CPR – 2323**.

The system of quality is conform with EN ISO 9001 .

*-the length depends on weight