



806 DOOR & WINDOW POLYURETHANE FOAM

Akfix 806 is a single-component, moisture-curing and self-expanding aerosol polyurethane foam. It is designed for easy dispensing through the straw adapter included with each can. It is designed for **easy filling of door and window profiles with low expansion and pressure rates.**

FEATURES & BENEFITS

- Excellent adhesion & filling capacity and high thermal & acoustical insulation value.
- Low expansion, low pressure rates.
- Adheres to almost all building materials with the exception of surfaces such as polyethylene, Teflon, silicone and surfaces contaminated with oils and greases, mold release agents and similar materials.
- Mould-proof, water-proof, over paintable.
- Cured foam dries rigid and can be trimmed, shaped and sanded.

APPLICATIONS

- Fixing and insulating of door and window frames.
- Filling and sealing gaps, joints and cavities.
- Filling of penetrations in walls.
- Insulating electrical outlets and water pipes.

INSTRUCTIONS

- Optimal can temperature is +20 °C. Application (ambient) temperature is between -5 °C to +30 °C.
- Shake the can well before use. Screw the adapter on the valve.
- Hold the can upside down and activate the foam by pressing the valve.
- Moisturizing the surfaces and the foam improves adhesion and shortens curing time.
- Fresh foam can be cleaned by Akfix Foam Cleaner. Cured foam can be cleaned barely mechanically.

STANDARDS

Meets or exceeds the requirements of the following specifications:

- The French VOC requirements for class A+
- UL listed.
- The requirements of VOC content specifications in LEED credit EQc4.1 "Low-emitting products" of SCAQMD rule 1168.



Low
Expansion,
Easy
Usage



RESTRICTIONS

- Storage above +25 °C and below +5 °C shortens shelf life.
- Should be stored and transported in vertical position.
- Should be kept in room temperature for at least 12 hours before the application.
- Cured foam will discolor if exposed to ultraviolet light.
- Paint or coat the cured foam for best results in outdoor applications.
- Lower temperatures decrease yield and curing time.

SAFETY

- Contains Diphenylmethane-4, 4'-Diisocyanate.
- Harmful by inhalation. Irritating to eyes, respiratory system and skin. Do not breathe spray/vapour.
- Wear suitable protective clothing and gloves. Use only in well-ventilated areas.
- Pressurized container. Keep away from direct sunlight and do not expose temperatures over 50 °C.
- Do not pierce or burn, even after use.
- Keep away from sources of ignition, no smoking.
- Keep out of the reach of children.

STORAGE AND SHELF LIFE

- 12 months if stored properly.

PROPERTIES

Basis	: Polyurethane Prepolymer	
Curing System	: Moisture cure	
Specific Gravity	: 22±3 Kg/m ³	(ASTM D1622)
Tack-Free Time (1 cm width)	: 7±2 min	(ASTM C1620)
Cutting Time (1cm width)	: 20-45 min	(ASTM C1620)
Cure-Time	: 24 hours	
Foam Color	: Light yellow	
Yield	: 30-45 L	(ASTM C1536)
Fire Class of the Cured Foam	: B3	(DIN 4102-1)
Thermal Conductivity	: 0,036 W/m.k (at 20°C)	(DIN 52612)
Compression Strength	: 0,03 MPa	(DIN 53421)
Water Penetration	: 0	(ISO 2896-87)
Water Absorption	: max. 1 vol%	(DIN 53428)
Can Temperature	: min.5°C max. +30°C	
Temperature Resistance	: -40°C to +80°C	
Application Temperature	: +5°C to +30°C	

The results were obtained by providing optimum environmental conditions.



PACKAGING

Product	Weight	Package
806	850gr.	12

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.