


Insulated Bubble Cushioning DB

PRODUCT SPECIFICATION SHEET

REFLECTIVE INSULATION

PHYSICAL PROPERTIES	UNIT	VALUE	TOLERANCES
Description	-	Foil + AirCap® + Cell-Aire® 1.5mm + AirCap® + Foil 	
Nominal Thickness	mm	7.5	+/- 10%
Aluminium Foil Thickness	-	7MY + 22MY PE	-
Operating Temperature	°C	-51 - +81	-
Aluminium Foil Purity	%	99.9	-
Aluminium Foil Reflectivity	%	95-97	-
Foil Anti-Corrosion Coating	-	NC lacquer	-
AirCap® Bubble Density	gr/m ²	90	+/- 5%
Total Product Density	gr/m ²	285	+/- 5%
Rolls Size	m/m ²	1.20m x 25m = 30m ²	-
U Value	W/m ²	1.11	-
Test Method	-	UNE-EN ISO 8990:1997	-
Testing Facility	-	Cidemco/Spain	-
Flame Resistance	-	B2	-
Test Method	-	DIN 4102	-
Testing Facility	-	Firelabs/Germany	-

NOTICE: While values shown are typical of this product, they should not be construed as specification limits. Sealed Air makes no warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, with respect to any product, information or recommendations referred to herein, and shall not be liable for any loss or damage, directly or indirectly, related to such product, information or recommendations or for consequential or incidental damages. User should test each application to determine suitability of the product for the intended use.