

Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

Page 1/9

#### SECTION 1: Identification of the substance/mixture and of the company/ undertaking

· 1.1 Product identifier	
· Trade name	MC-Injekt 2700 L - Komponente A
<ul> <li>Article number:</li> <li>1.2 Relevant identified uses of the substance or mixture and uses advised against</li> <li>Application of the substance</li> </ul>	474 No further relevant information available.
/ the mixture	Sealant
• 1.3 Details of the supplier of the supplier of the supplier:	he safety data sheet MC-Bauchemie Müller GmbH & Co. KG Am Kruppwald 1-8 D-46238 Bottrop Tel.: +49(0)2041-101-0 Fax.: +49(0)2041-101-400 E-Mail: info@mc-bauchemie.de MC-Bauchemie AG Hagackerstr. 10 CH-8953 Dietikon Tel.: +44-7400510 Fax : +44-7400533
<ul> <li>Informing department:</li> <li>1.4 Emergency telephone number:</li> </ul>	msds@mc-bauchemie.de Tel.: +49 /  (0)700 24112112 (MCR) Tel.: +1 872 5888271 (MCR)
SECTION 2: Hazards iden • 2.1 Classification of the subst • Classification according to Regulation (EC) No 1272/2008	
<ul> <li>2.2 Label elements</li> <li>Labelling according to Regulation (EC) No 1272/2008</li> <li>Hazard pictograms</li> <li>Signal word</li> <li>Hazard statements</li> </ul>	

· Additional information: EUH210 Safety data sheet available on request.

- · 2.3 Other hazards
- · Results of PBT and vPvB assessment
- · PBT: Not applicable. · vPvB:
  - Not applicable.

(Contd. on page 2)

GB



Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

Trade name MC-Injekt 2700 L - Komponente A

(Contd. of page 1)

Page 2/9

# SECTION 3: Composition/information on ingredients · 3.2 Mixtures · Description: Resin mixture. Mixture consisting of the following components. · Dangerous components: CAS: 25322-69-4 Polypropylene glycol · Additional information For the wording of the listed hazard phrases refer to section 16.

**SECTION 4: First aid measures** 

<ul> <li>4.1 Description of first aid me</li> </ul>	asures
General information	Remove, decontaminate and dispose of soiled, soaked clothing and shoes immediately.
· After inhalation	Remove person to fresh air, keep warm, allow to rest; if breathing is difficult, seek medical attention.
· After skin contact	In case of contact with skin, preferably wash with polyethylene glycol-based cleaner or clean with plenty of warm water and soap. Consult a doctor in case of skin reactions.
· After eye contact	Rinse the eyes with open eyelids for a sufficiently long time (at least 10 minutes) with water that is as lukewarm as possible. Consult an ophthalmologist.
· After swallowing	Do NOT induce vomiting. Rinse mouth with water. Medical attention required.
<ul> <li>4.2 Most important symptoms and effects, both acute and</li> </ul>	; ;
delayed	Information for the doctor: The product irritates the respiratory tract and is a potential trigger for skin and respiratory sensitisation. Treatment of acute irritation or bronchial constriction is primarily symptomatic. Depending on the extent of exposure and the symptoms, prolonged medical treatment may be necessary.
<ul> <li>4.3 Indication of anv</li> </ul>	

4.3 Indication of any immediate medical attention and special treatment needed No information available.

#### **SECTION 5: Firefighting measures**

· 5.1 Extinguishing media

• Suitable extinguishing agents Use fire fighting measures that suit the environment.

- 5.2 Special hazards arising
- from the substance or mixture

No further relevant information available.

(Contd. on page 3)

GB



Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

(Contd. of page 2)

GB

Trade name MC-Injekt 2700 L - Komponente A

5.3 Advice for firefighters
 Protective equipment:

No special measures required.

#### SECTION 6: Accidental release measures

· 6.1 Personal precautions, protective equipment and	
emergency procedures	Not required.
6.2 Environmental	
precautions:	No special measures required.
• 6.3 Methods and material for	
containment and cleaning up:	Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).
• 6.4 Reference to other	
sections	No dangerous materials are released.

#### **SECTION 7: Handling and storage**

• 7.1 Precautions for safe	
handling	Ensure sufficient air exchange and/or extraction in the work areas. Air extraction is required for spray application. For solid products: Avoid dust formation and dust deposits. Air limit values mentioned in section 8 must be monitored. At workplaces where isocyanate aerosols and/or vapours can occur in higher concentrations, targeted air extraction must be used to prevent the occupational hygiene limit value from being exceeded. The air must be moved away from people. For products containing solvents: Explosion protection required. The personal protective measures described in section 8 must be observed. The protective measures required when handling isocyanates must be observed. Avoid contact with skin and eyes and inhalation of vapours. Keep away from food and beverages. Wash hands before breaks and at the end of work and apply skin protection ointment. Store work clothes separately. Remove soiled, soaked clothing immediately.
<ul> <li>7.2 Conditions for safe storage, including any incompatibilities</li> </ul>	Keep container dry and tightly closed. Further information on the storage conditions that must be observed for quality assurance reasons can be found in our technical data sheet.
<ul> <li>Storage</li> <li>Requirements to be met by storerooms and containers:</li> <li>Further information about storage conditions:</li> </ul>	Store only in the original container.
· Storage class	10
	(Contd. on page 4)





Page 4/9

# Safety data sheet according to UK REACH

Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

#### Trade name MC-Injekt 2700 L - Komponente A

Components with critical values that require monitoring at the workplace: The product does not contain any relevant quantities of material with critical values that have to be monitored at the workplace. Additional information: The lists that were valid during the compilation were used as basis 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures Keep away from food, drink and animal feed. Remove soiled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin. Breathing equipment: Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shore term work. If applicable, further recommendations for respiratory protection ab found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Butty rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): buty rubber. In case of rolonged or frequently repeated contact, a glove with protection class of 3 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher is recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove material be rolocated as and the expending on the type and material, the thickness must be mor than 0.35 mm during prolonged wer. Cherg polo	7.3 Specific end use(s)	(Contd. of page 3 (Contd. of page 3 (Contd. of page 3 )
Components with critical values that require monitoring at the workplace: The product does not contain any relevant quantities of material with critical values that have to be monitored at the workplace. Additional information: The lists that were valid during the compilation were used as basis 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures Keep away from food, drink and animal feed. Remove soiled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin. Breathing equipment: Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shore term work. If applicable, further recommendations for respiratory protection ab found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Butty rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): buty rubber. In case of rolonged or frequently repeated contact, a glove with protection class of 3 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher is recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove material be rolocated as and the expending on the type and material, the thickness must be mor than 0.35 mm during prolonged wer. Cherg polo	SECTION 8: Exposure	controls/personal protection
values that require monitoring at the workplace: The product does not contain any relevant quantities of materia with critical values that have to be monitored at the workplace. The lists that were valid during the compilation were used as basis 8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures Keep away from food, drink and animal feed. Remove soiled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin. Breathing equipment: Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shor term work. If applicable, further recommendations for respiratory protectio can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protective depending on the type and material, the thickness must be moi than 0.35 mm to ensure adequate protection in the event prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection in the event prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection revent with thickness of less than 0.35 mm during	8.1 Control parameters	
monitoring at the workplace:       The product does not contain any relevant quantities of materia with critical values that have to be monitored at the workplace.         Additional information:       The lists that were valid during the compilation were used as basis         8.2 Exposure controls       No further data; see section 7.         Individual protection measures, such as personal protective equipment         General protective and hygienic measures       Keep away from food, drink and animal feed.         Remove soiled, soaked clothing immediately.       Wash hands before breaks and at the end of work.         Avoid contact with eyes and skin.       Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks or combination filters A2-P2 (EN529) are recommended for shorterm work.         If applicable, further recommendations for respiratory protection can be found in the appendix.       In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.         Hand protection       Suitable materials for protective gloves; EN 374:         Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).       Note: suitable materials that provide sufficient protection for industrial cleaning with a protection class of 3 or higher i recommended (breakthrough tim greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher i recommended (breakthrough tim greater than 0.35 mm to ensure endequate protection in the event or the iso depends to a large extent on the type of glove materia las of the mat		
<ul> <li>with critical values that have to be monitored at the workplace.</li> <li>Additional information:</li> <li>The lists that were valid during the compilation were used as basis</li> <li>Appropriate engineering controls</li> <li>No further data; see section 7.</li> <li>Individual protection measures, such as personal protective equipment</li> <li>General protective and hygienic measures</li> <li>Keep away from food, drink and animal feed.</li> <li>Remove soiled, soaked clothing immediately.</li> <li>Wash hands before breaks and at the end of work.</li> <li>Avoid contact with eyes and skin.</li> <li>Breathing equipment:</li> <li>Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks or combination filters A2-P2 (ENS29) are recommended for shorter work.</li> <li>If applicable, further recommendations for respiratory protectio can be found in the appendix.</li> <li>In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.</li> <li>Suitable materials for protective gloves; EN 374:</li> <li>Butyl rubber, rithile rubber, chloroprene rubber (neoprene).</li> <li>Note: suitable materials that provide sufficient protection for industrial cleaning with a protection class of 3 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374).</li> <li>In case of ploonged or frequently repeated contact, a glove with protection class of the material is not the only criterion for the level i protection of the N374).</li> <li>The thickness of the material is not the only criterion for the level i protection or alloy eagenst a chemical substance. The protection for alloy estimate a depunde protection in the event or prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection reven with thickness of less than 0.35 mm during prolonged wear</li></ul>		
Additional information:       The lists that were valid during the compilation were used as basis         8.2 Exposure controls       No further data; see section 7.         Individual protection measures, such as personal protective equipment         General protective and         hygienic measures       Keep away from food, drink and animal feed.         Remove soiled, soaked clothing immediately.         Wash hands before breaks and at the end of work.         Avoid contact with eyes and skin.         Breathing equipment:         Respiratory protection required at insufficiently ventilate         workplaces and when working with splashes. Fresh air masks of         combination filters A2-P2 (ENS29) are recommended for shor         If applicable, further recommendations for respiratory protectio         can be found in the appendix.         In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.         Hand protection         Suitable materials for protective gloves; EN 374:         Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).         Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber.         In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to	monitoring at the workplace	
8.2 Exposure controls Appropriate engineering controls No further data; see section 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures Keep away from food, drink and animal feed. Remove soiled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin. Breathing equipment: Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for short term work. If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-terr contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove material Depending on the type and material, the thickness must be mou than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mulh layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:	Additional information:	
Appropriate engineering controls         No further data; see section 7.           Individual protection measures, such as personal protective equipment General protective and hygienic measures         Keep away from food, drink and animal feed. Remove soiled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin.           Breathing equipment:         Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shor term work.           Hand protection         If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher , recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be moi than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mul layer gloves, which guarantee sufficient protection even with thickne	Additional information:	The lists that were valid during the compliation were used as basis
controls       No further data; see section 7.         Individual protection measures, such as personal protective equipment         General protective and         hygienic measures         Keep away from food, drink and animal feed.         Remove soiled, soaked clothing immediately.         Wash hands before breaks and at the end of work.         Avoid contact with eyes and skin.         Breathing equipment:         Respiratory protection required at insufficiently ventilate         workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for short term work.         If applicable, further recommendations for respiratory protection can be found in the appendix.         In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.         Suitable materials for protective gloves; EN 374:         Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).         Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber.         In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 60 minute according to EN374).         The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protective floves flow and anot a large extent on the type of glove materia be pending on the	8.2 Exposure controls	
Individual protection measures, such as personal protective equipment General protective and hygienic measures Keep away from food, drink and animal feed. Remove soiled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin. Breathing equipment: Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shord term work. If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chrond bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-terr contact, a glove with a protection class of 3 or higher - recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level + protection of a glove against a chemical substance. The protection than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
General protective and hygienic measures       Keep away from food, drink and animal feed. Remove soiled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin.         Breathing equipment:       Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shor term work. If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.         Hand protection       Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 on higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be moo than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mul layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
hygienic measuresKeep away from food, drink and animal feed. Remove solled, soaked clothing immediately. Wash hands before breaks and at the end of work. Avoid contact with eyes and skin.Breathing equipment:Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shor term work. If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection f industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher i recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectio pepending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event u prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		ures, such as personal protective equipment
Remove soiled, soaked clothing immediately.         Wash hands before breaks and at the end of work.         Avoid contact with eyes and skin.         Breathing equipment:         Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shorterm work.         If applicable, further recommendations for respiratory protectio can be found in the appendix.         In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.         Suitable materials for protective gloves; EN 374:         Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).         Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber.         In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-tended (breakthrough time greater than 60 minute according to EN374).         The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protection for the clearing on the type and material, the thickness must be moth 0.35 mm to ensure adequate protection in the event is prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection or so this rule are mult layer gloves, which guarantee sufficient protection or the event of prolonged		Keen and free freed driets and an inset freed
Wash hands before breaks and at the end of work. Avoid contact with eyes and skin.Breathing equipment:Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for short term work.If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.Hand protectionSuitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protection fefect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mol than 0.35 mm to ensure adequate protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of ses than 0.35 mm only provid sufficient protection short periods of wear. For solvent-free products:	nygienic measures	
Avoid contact with eyes and skin. Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shor term work. If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minutes according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protection than 0.35 mm to ensure adequate protection in the event prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
Breathing equipment:       Respiratory protection required at insufficiently ventilate workplaces and when working with splashes. Fresh air masks or combination filters A2-P2 (EN529) are recommended for shorterm work.         If applicable, further recommendations for respiratory protection can be found in the appendix.       In case of hypersensitivity of the respiratory tract (asthma, chrond bronchitis), handling of the product is not recommended.         Hand protection       Suitable materials for protective gloves; EN 374:         Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).       Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber.         In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374).         The thickness of the material is not the only criterion for the level or protection of a glove against a chemical substance. The protective effect also depends to a large extent on the type of glove materiad Depending on the type and material, the thickness must be mont than 0.35 mm to ensure adequate protection even with thickness of less than 0.35 mm only provid sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection even with thickness of less than 0.35 mm only provid sufficient protectis is for short periods of wear. <td></td> <td></td>		
workplaces and when working with splashes. Fresh air masks of combination filters A2-P2 (EN529) are recommended for shor term work. If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be moi than 0.35 mm to ensure adequate protection in the even of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:	Breathing equipment:	
combination filters A2-P2 (EN529) are recommended for shor term work. If applicable, further recommendations for respiratory protectio can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection fo industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ter contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mo than 0.35 mm to ensure adequate protection in the even of prolonged and frequent contact. Exceptions to this rule are mul layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:	Dicatining equipment.	workplaces and when working with splashes. Fresh air masks
term work. If applicable, further recommendations for respiratory protection can be found in the appendix. In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended. Suitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough time greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minutes according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protective effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mond than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of periods of wear. For solvent-free products:		
<ul> <li>can be found in the appendix.</li> <li>In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.</li> <li>Suitable materials for protective gloves; EN 374:</li> <li>Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).</li> <li>Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber.</li> <li>In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher i recommended (breakthrough time greater than 60 minute according to EN374).</li> <li>The thickness of the material is not the only criterion for the level oprotection of a glove against a chemical substance. The protective effect also depends to a large extent on the type of glove materiat Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multilayer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provide sufficient protection for short periods of wear. For solvent-free products:</li> </ul>		
<ul> <li>can be found in the appendix.</li> <li>In case of hypersensitivity of the respiratory tract (asthma, chron bronchitis), handling of the product is not recommended.</li> <li>Suitable materials for protective gloves; EN 374:</li> <li>Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).</li> <li>Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber.</li> <li>In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher i recommended (breakthrough time greater than 60 minute according to EN374).</li> <li>The thickness of the material is not the only criterion for the level oprotection of a glove against a chemical substance. The protective effect also depends to a large extent on the type of glove materiat Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multilayer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provide sufficient protection for short periods of wear. For solvent-free products:</li> </ul>		If applicable, further recommendations for respiratory protectio
<ul> <li>bronchitis), handling of the product is not recommended.</li> <li>Suitable materials for protective gloves; EN 374:</li> <li>Butyl rubber, nitrile rubber, chloroprene rubber (neoprene).</li> <li>Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber.</li> <li>In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough time greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minutes according to EN374).</li> <li>The thickness of the material is not the only criterion for the level oprotection of a glove against a chemical substance. The protection of a glove against a chemical substance. The protection than 0.35 mm to ensure adequate protection in the event oprolonged and frequent contact. Exceptions to this rule are multilayer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:</li> </ul>		
Hand protectionSuitable materials for protective gloves; EN 374: Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough time greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minutes according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protection effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mol than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		In case of hypersensitivity of the respiratory tract (asthma, chron
Butyl rubber, nitrile rubber, chloroprene rubber (neoprene). Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protection effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the even of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
Note: suitable materials that provide sufficient protection for industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mol than 0.35 mm to ensure adequate protection in the even of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:	Hand protection	
industrial cleaning with aprotic polar solvents (according to IUPA definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
definition): butyl rubber. In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-tern contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
In case of prolonged or frequently repeated contact, a glove with protection class of 5 or higher is recommended (breakthrough tim greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
protection class of 5 or higher is recommended (breakthrough time greater than 240 minutes according to EN374). For short-ten contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
greater than 240 minutes according to EN374). For short-term contact, a glove with a protection class of 3 or higher recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
contact, a glove with a protection class of 3 or higher a recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be mon than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
recommended (breakthrough time greater than 60 minute according to EN374). The thickness of the material is not the only criterion for the level protection of a glove against a chemical substance. The protectiv effect also depends to a large extent on the type of glove materia Depending on the type and material, the thickness must be more than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provide sufficient protection for short periods of wear. For solvent-free products:		
according to EN374). The thickness of the material is not the only criterion for the level of protection of a glove against a chemical substance. The protective effect also depends to a large extent on the type of glove material Depending on the type and material, the thickness must be more than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi- layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provide sufficient protection for short periods of wear. For solvent-free products:		
The thickness of the material is not the only criterion for the level of protection of a glove against a chemical substance. The protective effect also depends to a large extent on the type of glove material Depending on the type and material, the thickness must be more than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi- layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glow materials with a thickness of less than 0.35 mm only provide sufficient protection for short periods of wear. For solvent-free products:		
effect also depends to a large extent on the type of glove material Depending on the type and material, the thickness must be more than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provide sufficient protection for short periods of wear. For solvent-free products:		The thickness of the material is not the only criterion for the level
Depending on the type and material, the thickness must be more than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glove materials with a thickness of less than 0.35 mm only provide sufficient protection for short periods of wear. For solvent-free products:		protection of a glove against a chemical substance. The protectiv
than 0.35 mm to ensure adequate protection in the event of prolonged and frequent contact. Exceptions to this rule are multi layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		effect also depends to a large extent on the type of glove materia
prolonged and frequent contact. Exceptions to this rule are mult layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
layer gloves, which guarantee sufficient protection even with thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
thickness of less than 0.35 mm during prolonged wear. Other glov materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
materials with a thickness of less than 0.35 mm only provid sufficient protection for short periods of wear. For solvent-free products:		
sufficient protection for short periods of wear. For solvent-free products:		
For solvent-free products:		<b>,</b>
		(Contd. on page s



Page 5/9

GB

### Safety data sheet according to UK REACH

Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

#### Trade name MC-Injekt 2700 L - Komponente A

	(Contd. of page 4)
	Example:
	Polychloroprene - CR: thickness ≥0.5mm; breakthrough time ≥480min.
	Nitrile rubber - NBR: thickness ≥0.35mm; breakthrough time ≥480min.
	Butyl rubber - IIR: thickness ≥0.5mm; breakthrough time ≥480min. Fluoro rubber - FKM: thickness ≥0.4mm; breakthrough time
	≥480min. Recommendation: Dispose of contaminated gloves.
· Material of gloves	Polychloroprene - CR
material of gioves	Nitrile rubber - NBR
	Butyl rubber - IIR
	Fluoro rubber - FKM
· Penetration time of glove	
material	Polychloroprene - CR: thickness ≥0.5mm; breakthrough time ≥480min.
	Butyl rubber - IIR: thickness ≥0.5mm; breakthrough time ≥480min.
	Fluoro rubber - FKM: Thickness >0.4mm; Breakthrough time >480min.
· Eye/face protection	Safety goggles with side protection in accordance with EN 166.
· Body protection:	Use chemical-resistant protective clothing.
	In case of hypersensitivity of the skin, handling the product is not recommended.

**SECTION 9: Physical and chemical properties** 

· General Information	Linkturelleur
· Colour:	Light yellow
· Smell:	Characteristic
<ul> <li>Melting point/freezing point:</li> </ul>	Not determined
· Boiling point or initial boiling point an	d
boiling range	>200 °C (CAS: 25322-69-4 Polypropylene glycol
· Flash point:	>200 °C
·pH	Not determined.
· Viscosity:	
· Kinematic viscosity	Not determined.
· dynamic at 20 °C:	274 mPas
· Solubility	
· Water:	Partly miscible
· Steam pressure at 25 °C:	0.1 hPa (CAS: 25322-69-4 Polypropylene glycol)
· Density and/or relative density	
· Density at 20 °C	1.01 g/cm³



Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

Page 6/9

Trade name MC-Injekt 2700 L - Komponente A

		(Contd. of page 5)
<sup>•</sup> 9.2 Other information		
· Appearance:		
· Form:	Fluid	
· Important information on protection of hea	alth	
and environment, and on safety.		
Self-inflammability:	Product is not selfigniting.	
· Explosive properties:	Product is not explosive.	
· Information with regard to physical haz	ard	
classes		
· Explosives	Void	
· Flammable gases	Void	
· Aerosols	Void	
· Oxidising gases	Void	
<sup>.</sup> Gases under pressure	Void	
Flammable liquids	Void	
Flammable solids	Void	
• Self-reactive substances and mixtures	Void	
· Pyrophoric liquids	Void	
Pyrophoric solids	Void	
• Self-heating substances and mixtures	Void	
<ul> <li>Substances and mixtures, which emit</li> </ul>		
flammable gases in contact with water	Void	
· Oxidising liquids	Void	
Oxidising solids	Void	
· Organic peroxides	Void	
Corrosive to metals	Void	
<ul> <li>Desensitised explosives</li> </ul>	Void	

10.1 Reactivity	No further relevant information available.	
10.2 Chemical stability		
Thermal decomposition /		
conditions to be avoided:	No decomposition if used according to specifications.	
10.3 Possibility of hazardous		
reactions	No dangerous reactions known	
10.4 Conditions to avoid	No further relevant information available.	
10.5 Incompatible materials:	No further relevant information available.	
10.6 Hazardous		
decomposition products:	No dangerous decomposition products known	

(Contd. on page 7)



Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

Trade name MC-Injekt 2700 L - Komponente A

(Contd. of page 6)

Page 7/9

#### SECTION 11: Toxicological information

· 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008

• Acute toxicity Based on available data, the classification criteria are not met.

#### · LD/LC50 values that are relevant for classification:

CAS: 25322-69-4 Polypropylene glycol

Oral LD50 1000-<2000 mg/kg (rat)

Dermal LD50 >2000 mg/kg (rabbit)

Primary irritant effect:	
Skin corrosion/irritation	Based on available data, the classification criteria are not met.
· Serious eye damage/irritation	Based on available data, the classification criteria are not met.
· Respiratory or skin	
sensitisation	Based on available data, the classification criteria are not met.
· Germ cell mutagenicity	Based on available data, the classification criteria are not met.
· Carcinogenicity	Based on available data, the classification criteria are not met.
· Reproductive toxicity	Based on available data, the classification criteria are not met.
STOT-single exposure	Based on available data, the classification criteria are not met.
STOT-repeated exposure	Based on available data, the classification criteria are not met.
Aspiration hazard	Based on available data, the classification criteria are not met.
11.2 Information on other haza	ards
<ul> <li>Endocrine disrupting properti</li> </ul>	es

None of the ingredients is listed.

#### **SECTION 12: Ecological information**

· 12.1 Toxic	city	
· Aquatic to	oxicity:	
CAS: 2532	22-69-4 Polypropyle	ne glycol
LC50/48h	>100 mg/l (Leucidus	a idus)
EC50/48h	>100 mg/l (Daphnia	magna)
EC0	>100 mg/l (Desmod	esmus subspicatus)
degradab	ccumulative	No further relevant information available. No further relevant information available. No further relevant information available.
	Its of PBT and vPvB	
· PBT: · vPvB: · 12.6 Endo	crine disrupting	Not applicable. Not applicable.
properties	5	The product does not contain substances with endocrine disrupting properties.
		(Contd. on page 8)



Page 8/9

### Safety data sheet according to UK REACH

Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

(Contd. of page 7)

Trade name MC-Injekt 2700 L - Komponente A

12.7 Other adverse effects

- · Additional ecological information:
- · General notes:

Do not allow undiluted product or large quantities of it to reach ground water, water bodies or sewage system.

#### **SECTION 13: Disposal considerations**

13.1 Waste treatment methods
 Recommendation

Must not be disposed of together with household garbage. Do not allow product to reach sewage system.

Uncleaned packagings:
 Recommendation:

Empty contaminated packagings thoroughly. They can be recycled after thorough and proper cleaning.

SECTION 14: Transport informa	tion	
14.1 UN number or ID number ADR, ADN, IMDG, IATA	Void	
14.2 UN proper shipping name ADR, ADN, IMDG, IATA	Void	
14.3 Transport hazard class(es)		
ADR, ADN, IMDG, IATA Class	Void	
14.4 Packing group ADR, IMDG, IATA	Void	
14.5 Environmental hazards: Marine pollutant:	No	
14.6 Special precautions for user	Not applicable.	
<i>14.7 Maritime transport in bulk accordi IMO instruments</i>	ing to Not applicable.	
UN "Model Regulation":	Void	

#### SECTION 15: Regulatory information

 15.1 Safety, health and environmental regulations/ legislation specific for the substance or mixture

No further relevant information available.

(Contd. on page 9)

GB



Printing date 02.05.2025

Version number 36 (replaces version 35)

Revision: 02.05.2025

Page 9/9

#### Trade name MC-Injekt 2700 L - Komponente A

Poisons Act	(Contd. of page
Regulated explosives precurs	ors
None of the ingredients is listed.	
Regulated poisons	
None of the ingredients is listed.	
Reportable explosives precurs	
None of the ingredients is listed.	
Reportable poisons	
None of the ingredients is listed.	
15.2 Chemical safety assessment:	A Chemical Safety Assessment has not been carried out.
	esent knowledge. However, they shall not constitute a guarantee d shall not establish a legally valid contractual relationship.
Relevant phrases	H302 Harmful if swallowed.
Department issuing data specification sheet: Abbreviations and acronyms:	Environment protection department. RID: Règlement international concernant le transport des marchandis dangereuses par chemin de fer (Regulations Concerning the Internatio Transport of Dangerous Goods by Rail) ICAO: International Civil Aviation Organisation ADR: Accord relatif au transport international des marchandises dangereuses route (European Agreement Concerning the International Carriage of Dangero Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: Chemical Abstracts Service (division of the American Chemical Society) LC50: Lethal concentration, 50 percent LD50: Lethal dose, 50 percent PBT: Persistent, Bioaccumulative and Toxic vPvB: very Persistent and very Bioaccumulative
	Acute Tox. 4: Acute toxicity – Category 4
* Data compared to the previous version altered.	